

## TECHNICAL AND ENVIRONMENTAL SPECIFICATIONS

### CHARACTERISTICS

|                             | Standard | Tarkett value                             |
|-----------------------------|----------|---|
| <b>Construction Process</b> | ISO 2424 | TUFTED                                    |
| <b>Total thickness</b>      | -        | 0.225 " (5.77 mm)                         |
| <b>Installation method</b>  | -        | Glue-Down                                 |
| <b>Format Type</b>          | -        | Roll                                      |
| <b>Commercial warranty</b>  | -        | 10 year limited                           |
| <b>Surface treatment</b>    | -        | Eco-Ensure(Fluorine-Free Soil Protection) |
| <b>Secondary backing</b>    | ISO 2424 | Super-Lok®                                |
| <b>Pile construction</b>    | -        | Textured loop pile                        |
| <b>Gauge</b>                | -        | 1/10"                                     |
| <b>Face Weight</b>          | -        | 22 oz/yd <sup>2</sup>                     |
| <b>Pile density</b>         | ISO 8543 | 6326 oz/yd <sup>3</sup>                   |
| <b>Dye Method</b>           | -        | Solution dyed                             |
| <b>Primary backing</b>      | -        | Woven Polypropylene                       |
| <b>Fiber System</b>         | ISO 2424 | Dynex SD® Nylon                           |

### TECHNICAL PERFORMANCE

|                                 | Standard | Tarkett value                             |
|---------------------------------|----------|---|
| <b>Flammability</b>             | -        | Class 1 ( $\geq 0.45$ W/cm <sup>2</sup> ) |
| <b>Electrostatic Propensity</b> | -        | $\leq 3.5$ kV                             |
| <b>Colorfastness to Light</b>   | -        | $\geq 4$ after 100 hours                  |
| <b>Is cuttable</b>              | -        | Yes                                       |

### SUSTAINABILITY, ENVIRONMENT & INDOOR AIR QUALITY

|  | Standard | Tarkett value  |
|--|----------|--|
| <b>CRI Green Label Plus Certification</b>  | -        | GLP0025  |
| <b>ReStart®</b>                            | -        | Yes  |
| <b>Antimicrobial Chemicals</b>             | -        | No antimicrobials (EPA Registered pesticides) added to product |
| <b>Recycled Content - Production Waste</b> | -        | 0 %  |
| <b>Post Consumer recycled content</b>      | -        | 0 %  |

### CHARACTERISTICS & TECHNICAL PERFORMANCE

|                             | Standard     | Tarkett value                          |
|-----------------------------|--------------|--|
| <b>Maximum pile height</b>  | -            | 0.1770 " (4.50 mm)                     |
| <b>Soil protection</b>      | -            | Application Rate: 2% of Face Weight    |
| <b>Pile construction</b>    | -            | Textured loop pile                     |
| <b>Stain Resistance</b>     | AATCC 175-08 | $\geq 8$                               |
| <b>Surface Flammability</b> | -            | Meets CAN/CGSB-4.2 No.27.6/DOC FF 1-70 |

|                                 | Standard  | Tarkett value                             |
|---------------------------------|-----------|---|
| <b>Total thickness</b>          | ASTM F386 | 0.225 " (5.77 mm)                         |
| <b>Electrostatic Propensity</b> | -         | ≤ 3.5 kV                                  |
| <b>Gauge</b>                    | -         | 1/10"                                     |
| <b>Colorfastness to Light</b>   | AATCC 16E | ≥ 4 after 100 hours                       |
| <b>Stitches/Rows per Inch</b>   | -         | 12 /in                                    |
| <b>Minimum pile height</b>      | -         | 0.0980 " (2.49 mm)                        |
| <b>Pile density</b>             | -         | 6326 oz/yd <sup>3</sup>                   |
| <b>Fiber System</b>             | -         | Dynex SD® Nylon                           |
| <b>Dye Method</b>               | -         | Solution dyed                             |
| <b>Secondary backing</b>        | -         | Super-Lok®                                |
| <b>Primary backing</b>          | -         | Woven Polypropylene                       |
| <b>Installation method</b>      | -         | Glue-Down                                 |
| <b>Pattern</b>                  | -         | Grama II 44025                            |
| <b>Pattern type</b>             | -         | Texture                                   |
| <b>Pattern scale</b>            | -         | Small                                     |
| <b>Pattern match</b>            | -         | Yes                                       |
| <b>Pattern repeat length</b>    | -         | 0.30 "                                    |
| <b>Pattern repeat width</b>     | -         | 0.20 "                                    |
| <b>Format Type</b>              | -         | Roll                                      |
| <b>Commercial warranty</b>      | -         | 10 year limited                           |
| <b>Flammability</b>             | ASTM E648 | Class 1 (≥ 0.45 W/cm <sup>2</sup> )       |
| <b>Smoke Density</b>            | ASTM E662 | < 450                                     |
| <b>Surface treatment</b>        | -         | Eco-Ensure(Fluorine-Free Soil Protection) |
| <b>Type of product</b>          | -         | Textile Flooring                          |
| <b>Length</b>                   | -         | 1800 "                                    |
| <b>Width</b>                    | -         | 144 "                                     |