

TECHNICAL AND ENVIRONMENTAL SPECIFICATIONS

CHARACTERISTICS

	Standard	Tarkett value
Total thickness	-	0.365 " (9.3 mm)
Pile thickness	ISO 1766	0.095 " (2.46 mm)
Fiber System	ISO 2424	Dynex SD® Nylon
Format Type	-	Roll
Construction Process	ISO 2424	TUFTED
Installation method	-	Glue-Down
Commercial warranty	-	10 year limited
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Secondary backing	ISO 2424	ErgoStep®
Pile construction	-	Patterned Tipshear
Gauge	-	1/10"
Face Weight	-	23 oz/yd ²
Pile density	ISO 8543	5671 oz/yd ³
Dye Method	-	Solution dyed
Primary backing	-	Woven Polypropylene

TECHNICAL PERFORMANCE

	Standard	Tarkett value
Flammability	-	Class 2 (mean average 0.22 w/cm ² to 0.44 w/cm ²)
Electrostatic Propensity	-	≤ 3.5 kV
Colorfastness to Light	-	≥ 4 after 100 hours
Is cutable	-	Yes
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Total thickness	-	0.365 " (9.3 mm)
Installation method	-	Glue-Down
Format Type	-	Roll

SUSTAINABILITY, ENVIRONMENT & INDOOR AIR QUALITY

	Standard	Tarkett value
ReStart®	-	Yes
CRI Green Label Plus Certification	-	GLP7544
Recycled Content - Production Waste	-	0 %
Antimicrobial Chemicals	-	No antimicrobials (EPA Registered pesticides) added to product
Post Consumer recycled content	-	8 %

CHARACTERISTICS & TECHNICAL PERFORMANCE

	Standard	Tarkett value
--	----------	---------------

	Standard	Tarkett value
Total thickness	ASTM F386	0.365 " (9.3 mm)
Type of product	-	Textile Flooring
Length	-	1800 "
Width	-	144 "
Pattern	-	Loci III 44030
Commercial warranty	-	10 year limited
Flammability	ASTM E648	Class 2 (mean average 0.22 w/cm ² to 0.44 w/cm ²)
Smoke Density	ASTM E662	< 450
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Installation method	-	Glue-Down
Pattern type	-	Texture
Format Type	-	Roll
Soil protection	-	Application Rate: 2% of Face Weight
Maximum pile height	-	0.1770 " (4.50 mm)
Stain Resistance	AATCC 175-08	≥8
Pile construction	-	Patterned Tipshear
Surface Flammability	-	Meets CAN/CGSB-4.2 No.27.6/DOC FF 1-70
Electrostatic Propensity	-	≤ 3.5 kV
Gauge	-	1/10"
Colorfastness to Light	AATCC 16E	≥ 4 after 100 hours
Stitches/Rows per Inch	-	8.10 /in
Pile thickness	ASTM D5848	0.095 " (2.46 mm)
Minimum pile height	-	0.0970 " (2.46 mm)
Pile density	-	5671 oz/yd ³
Fiber System	-	Dynex SD® Nylon
Dye Method	-	Solution dyed
Secondary backing	-	ErgoStep®
Primary backing	-	Woven Polypropylene
Pattern repeat length	-	7.90 "
Pattern repeat width	-	0.40 "