

## TECHNICAL AND ENVIRONMENTAL SPECIFICATIONS

### CHARACTERISTICS

	Standard	Tarkett value
<b>Total thickness</b>	-	0.285 " (7.2 mm)
<b>Pile thickness</b>	ISO 1766	0.100 " (2.59 mm)
<b>Fiber System</b>	ISO 2424	Dynex SD® Nylon
<b>Format Type</b>	-	Tile
<b>Construction Process</b>	ISO 2424	TUFTED
<b>Installation method</b>	-	Peel & Stick
<b>Commercial warranty</b>	-	Lifetime Limited
<b>Surface treatment</b>	-	Eco-Ensure(Fluorine-Free Soil Protection)
<b>Secondary backing</b>	ISO 2424	Modular ER3® RS
<b>Pile construction</b>	-	Patterned Tipshear
<b>Gauge</b>	-	5/64"
<b>Face Weight</b>	-	25 oz/yd <sup>2</sup>
<b>Dye Method</b>	-	Solution dyed
<b>Primary backing</b>	-	Synthetic Non-Woven

### TECHNICAL PERFORMANCE

	Standard	Tarkett value
<b>Flammability</b>	-	Class 1 ( $\geq 0.45$ W/cm <sup>2</sup> )
<b>Electrostatic Propensity</b>	-	$\leq 3.0$ kV
<b>Is cuttable</b>	-	No
<b>Total thickness</b>	-	0.285 " (7.2 mm)
<b>Installation method</b>	-	Peel & Stick
<b>Format Type</b>	-	Tile

### SUSTAINABILITY, ENVIRONMENT & INDOOR AIR QUALITY

	Standard	Tarkett value
<b>ReStart®</b>	-	Yes
<b>CRI Green Label Plus Certification</b>	-	GLP1366
<b>Recycled Content - Production Waste</b>	-	30 %
<b>Third Party Certification NSF-140</b>	-	Gold
<b>Antimicrobial Chemicals</b>	-	No antimicrobials (EPA Registered pesticides) added to product
<b>Post Consumer recycled content</b>	-	22 %

### CHARACTERISTICS & TECHNICAL PERFORMANCE

	Standard	Tarkett value
<b>Total thickness</b>	ASTM F386	0.285 " (7.2 mm)
<b>Type of product</b>	-	Textile Flooring

	Standard	Tarkett value
<b>Pattern</b>	-	Avant 04840
<b>Commercial warranty</b>	-	Lifetime Limited
<b>Flammability</b>	ASTM E648	Class 1 ( $\geq 0.45$ W/cm <sup>2</sup> )
<b>Smoke Density</b>	ASTM E662	450 or Less
<b>Surface treatment</b>	-	Eco-Ensure(Fluorine-Free Soil Protection)
<b>Installation method</b>	-	Peel & Stick
<b>Pattern type</b>	-	Organic
<b>Format Type</b>	-	Tile
<b>Construction</b>	-	Stratatec® Patterned Syntex®
<b>Soil protection</b>	-	Application Rate: 2% of Face Weight
<b>Stain Resistance</b>	AATCC 175-08	$\geq 8$
<b>Pile construction</b>	-	Patterned Tipshear
<b>Surface Flammability</b>	-	Meets CAN/CGSB-4.2 No.27.6/DOC FF 1-70
<b>Electrostatic Propensity</b>	-	$\leq 3.0$ kV
<b>Gauge</b>	-	5/64"
<b>Stitches/Rows per Inch</b>	-	10.40 /in
<b>Pile thickness</b>	ASTM D5848	0.100 " (2.59 mm)
<b>Average pile height</b>	-	0.185 " (5 mm)
<b>Fiber System</b>	-	Dynex SD® Nylon
<b>Dye Method</b>	-	Solution dyed
<b>Secondary backing</b>	-	Modular ER3® RS
<b>Primary backing</b>	-	Synthetic Non-Woven
<b>Pattern scale</b>	-	Large
<b>Pattern match</b>	-	Yes
<b>Pattern repeat length</b>	-	94.23 "
<b>Pattern repeat width</b>	-	72 "