

TECHNICAL AND ENVIRONMENTAL SPECIFICATIONS

CHARACTERISTICS

	Standard	Tarkett value
Total thickness	-	0.355 " (9 mm)
Pile thickness	ISO 1766	0.100 " (2.59 mm)
Fiber System	ISO 2424	Dynex SD® Nylon
Format Type	-	Roll
Construction Process	ISO 2424	TUFTED
Installation method	-	Glue-Down
Commercial warranty	-	Lifetime Limited
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Secondary backing	ISO 2424	Powerbond Cushion
Pile construction	-	Patterned Tipshear
Gauge	-	5/64"
Face Weight	-	25 oz/yd ²
Pile density	ISO 8543	8824 oz/yd ³
Dye Method	-	Solution dyed
Primary backing	-	Synthetic Non-Woven

TECHNICAL PERFORMANCE

	Standard	Tarkett value
Flammability	-	Class 1 (≥ 0.45 W/cm ²)
Electrostatic Propensity	-	≤ 3.0 kV
Is cuttable	-	Yes
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Total thickness	-	0.355 " (9 mm)
Installation method	-	Glue-Down
Format Type	-	Roll

SUSTAINABILITY, ENVIRONMENT & INDOOR AIR QUALITY

	Standard	Tarkett value
ReStart®	-	Yes
CRI Green Label Plus Certification	-	GLP9744
Recycled Content - Production Waste	-	0 %
Third Party Certification NSF-140	-	Gold
Antimicrobial Chemicals	-	No antimicrobials (EPA Registered pesticides) added to product
Post Consumer recycled content	-	9 %

CHARACTERISTICS & TECHNICAL PERFORMANCE

	Standard	Tarkett value
--	----------	---------------

	Standard	Tarkett value
Total thickness	ASTM F386	0.355 " (9 mm)
Type of product	-	Textile Flooring
Length	-	1260 "
Width	-	72 "
Pattern	-	Avant 04840
Commercial warranty	-	Lifetime Limited
Flammability	ASTM E648	Class 1 (≥ 0.45 W/cm ²)
Smoke Density	ASTM E662	450 or Less
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Installation method	-	Glue-Down
Pattern type	-	Organic
Format Type	-	Roll
Construction	-	Stratatec® Patterned Symtex®
Soil protection	-	Application Rate: 2% of Face Weight
Stain Resistance	AATCC 175-08	≥ 8
Pile construction	-	Patterned Tipshear
Surface Flammability	-	Meets CAN/CGSB-4.2 No.27.6/DOC FF 1-70
Electrostatic Propensity	-	≤ 3.0 kV
Gauge	-	5/64"
Stitches/Rows per Inch	-	10.40 /in
Pile thickness	ASTM D5848	0.100 " (2.59 mm)
Average pile height	-	0.185 " (5 mm)
Pile density	-	8824 oz/yd ³
Fiber System	-	Dynex SD® Nylon
Dye Method	-	Solution dyed
Secondary backing	-	Powerbond Cushion
Primary backing	-	Synthetic Non-Woven
Pattern scale	-	Large
Pattern match	-	Yes
Pattern repeat length	-	94.23 "
Pattern repeat width	-	72 "