

TECHNICAL AND ENVIRONMENTAL SPECIFICATIONS

CLASSIFICATION

	Standard	Tarkett value
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Total thickness	ASTM F386	0.245 " (6.3 mm)
Pattern	-	ColorKnit 11128
Pattern type	-	Texture
Commercial warranty	-	Lifetime Limited
Flammability	ASTM E648	Class 1 (≥ 0.45 W/cm ²)
Smoke Density	ASTM E662	450 or Less

CHARACTERISTICS

	Standard	Tarkett value
Total thickness	-	0.245 " (6.3 mm)
Pile thickness	ISO 1766	0.095 " (2.41 mm)
Fiber System	ISO 2424	TDX® Nylon
Construction Process	ISO 2424	TUFTED
Installation method	-	Glue-Down
Commercial warranty	-	Lifetime Limited
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Secondary backing	ISO 2424	ethos® Modular with Omnicoat Technology™
Pile construction	-	Patterned loop pile
Gauge	-	5/64"
Face Weight	-	23 oz/yd ²
Dye Method	-	Solution dyed
Primary backing	-	Synthetic Non-Woven
Cradle-to-Cradle	-	Silver
DECLARE	-	Yes

TECHNICAL PERFORMANCE

	Standard	Tarkett value
Flammability	-	Class 1 (≥ 0.45 W/cm ²)
Electrostatic Propensity	-	≤ 3.0 kV
Is cuttable	-	No

SUSTAINABILITY, ENVIRONMENT & INDOOR AIR QUALITY

	Standard	Tarkett value
Cradle-to-Cradle	-	Silver
ReStart®	-	Yes
CRI Green Label Plus Certification	-	GLP8320

	Standard	Tarkett value
DECLARE	-	Yes
Recycled Content - Production Waste	-	23 %
Third Party Certification NSF-140	-	Platinum
Antimicrobial Chemicals	-	No antimicrobials (EPA Registered pesticides) added to product
Post Consumer recycled content	-	33 %

CHARACTERISTICS & TECHNICAL PERFORMANCE

	Standard	Tarkett value
Total thickness	ASTM F386	0.245 " (6.3 mm)
Type of product	-	Textile Flooring
Pattern	-	ColorKnit 11128
Commercial warranty	-	Lifetime Limited
Flammability	ASTM E648	Class 1 (≥ 0.45 W/cm ²)
Smoke Density	ASTM E662	450 or Less
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Installation method	-	Glue-Down
Pattern type	-	Texture
Construction	-	Stratatec® Patterned Loop
Soil protection	-	Application Rate: 2% of Face Weight
Pile construction	-	Patterned loop pile
Surface Flammability	-	Meets CAN/CGSB-4.2 No.27.6/DOC FF 1-70
Electrostatic Propensity	-	≤ 3.0 kV
Gauge	-	5/64"
Stitches/Rows per Inch	-	8.40 /in
Pile thickness	ASTM D5848	0.095 " (2.41 mm)
Average pile height	-	0.155 " (4 mm)
Fiber System	-	TDX® Nylon
Dye Method	-	Solution dyed
Secondary backing	-	ethos® Modular with Omniccoat Technology™
Primary backing	-	Synthetic Non-Woven
Pattern scale	-	Small
Pattern match	-	No
Pattern repeat length	-	44.44 "
Pattern repeat width	-	18.13 "