

## TECHNICAL AND ENVIRONMENTAL SPECIFICATIONS

### CHARACTERISTICS

	Standard	Tarkett value
<b>Total thickness</b>	-	0.080 " (2 mm)
<b>Pile thickness</b>	ISO 1766	0.195 " (5 mm)
<b>Fiber System</b>	ISO 2424	Dynex SD® Nylon
<b>Format Type</b>	-	Roll
<b>Construction Process</b>	ISO 2424	TUFTED
<b>Installation method</b>	-	Glue-Down
<b>Commercial warranty</b>	-	20 year limited
<b>Surface treatment</b>	-	Eco-Ensure(Fluorine-Free Soil Protection)
<b>Secondary backing</b>	ISO 2424	LifeLONG®
<b>Pile construction</b>	-	Patterned loop pile
<b>Gauge</b>	-	5/64"
<b>Pile density</b>	ISO 8543	7255 oz/yd <sup>3</sup>
<b>Dye Method</b>	-	Solution dyed
<b>Primary backing</b>	-	Woven Polypropylene

### TECHNICAL PERFORMANCE

	Standard	Tarkett value
<b>Flammability</b>	-	Class 1 ( $\geq 0.45$ W/cm <sup>2</sup> )
<b>Electrostatic Propensity</b>	-	$\leq 3.5$ kV
<b>Colorfastness to Light</b>	-	$\geq 4$ after 100 hours
<b>Is cuttable</b>	-	Yes

### SUSTAINABILITY, ENVIRONMENT & INDOOR AIR QUALITY

	Standard	Tarkett value
<b>ReStart®</b>	-	Yes
<b>CRI Green Label Plus Certification</b>	-	GLP100160
<b>Recycled Content - Production Waste</b>	-	28 %
<b>Antimicrobial Chemicals</b>	-	No antimicrobials (EPA Registered pesticides) added to product
<b>Post Consumer recycled content</b>	-	0 %

### CHARACTERISTICS & TECHNICAL PERFORMANCE

	Standard	Tarkett value
<b>Total thickness</b>	ASTM F386	0.080 " (2 mm)
<b>Type of product</b>	-	Textile Flooring
<b>Length</b>	-	1800 "
<b>Width</b>	-	150 "
<b>Pattern</b>	-	Terrace 40050

	Standard	Tarkett value
<b>Commercial warranty</b>	-	20 year limited
<b>Flammability</b>	ASTM E648	Class 1 ( $\geq 0.45$ W/cm <sup>2</sup> )
<b>Smoke Density</b>	ASTM E662	< 450
<b>Surface treatment</b>	-	Eco-Ensure(Fluorine-Free Soil Protection)
<b>Installation method</b>	-	Glue-Down
<b>Pattern type</b>	-	Organic
<b>Format Type</b>	-	Roll
<b>Soil protection</b>	-	Application Rate: 2% of Face Weight
<b>Maximum pile height</b>	-	0.1970 " (5 mm)
<b>Stain Resistance</b>	AATCC 175-08	$\geq 8$
<b>Pile construction</b>	-	Patterned loop pile
<b>Surface Flammability</b>	-	Meets CAN/CGSB-4.2 No.27.6/DOC FF 1-70
<b>Electrostatic Propensity</b>	-	$\leq 3.5$ kV
<b>Gauge</b>	-	5/64"
<b>Colorfastness to Light</b>	AATCC 16E	$\geq 4$ after 100 hours
<b>Stitches/Rows per Inch</b>	-	12.10 /in
<b>Pile thickness</b>	ASTM D5848	0.195 " (5 mm)
<b>Minimum pile height</b>	-	0.0790 " (2.01 mm)
<b>Pile density</b>	-	7255 oz/yd <sup>3</sup>
<b>Fiber System</b>	-	Dynex SD® Nylon
<b>Dye Method</b>	-	Solution dyed
<b>Secondary backing</b>	-	LifeLONG®
<b>Primary backing</b>	-	Woven Polypropylene
<b>Pattern repeat length</b>	-	51.24 "
<b>Pattern repeat width</b>	-	18.75 "