

TECHNICAL AND ENVIRONMENTAL SPECIFICATIONS

CLASSIFICATION

	Standard	Tarkett value
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Flammability	ASTM E648	Class 1 (≥ 0.45 W/cm ²)
Smoke Density	ASTM E662	< 450
Pattern	-	Solana K0120
Pattern type	-	Organic
Format Type	-	Roll
Commercial warranty	-	10 year limited

CHARACTERISTICS

	Standard	Tarkett value
Pile thickness	ISO 1766	0.235 " (5.94 mm)
Fiber System	ISO 2424	Dynex SD® Nylon
Format Type	-	Roll
Commercial warranty	-	10 year limited
Construction Process	ISO 2424	TUFTED
Installation method	-	Glue-Down
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Secondary backing	ISO 2424	ERGO-BLOK
Dye Method	-	Solution dyed
Primary backing	-	Woven Polypropylene
Pile construction	-	Patterned Tipshear
Gauge	-	1/10"
Face Weight	-	30 oz/yd ²
Pile density	ISO 8543	9143 oz/yd ³
ReStart®	-	Yes
Recycled Content - Production Waste	-	18.2 %
Post Consumer recycled content	-	4.4 %

TECHNICAL PERFORMANCE

	Standard	Tarkett value
Flammability	-	Class 1 (≥ 0.45 W/cm ²)
Electrostatic Propensity	-	≤ 3.5 kV
Colorfastness to Light	-	≥ 4 after 100 hours
Is cuttable	-	Yes

SUSTAINABILITY, ENVIRONMENT & INDOOR AIR QUALITY

	Standard	Tarkett value
--	----------	---------------

	Standard	Tarkett value
ReStart®	-	Yes
Recycled Content - Production Waste	-	18.2 %
Antimicrobial Chemicals	-	No antimicrobials (EPA Registered pesticides) added to product
Post Consumer recycled content	-	4.4 %

CHARACTERISTICS & TECHNICAL PERFORMANCE

	Standard	Tarkett value
Type of product	-	Textile Flooring
Length	-	1800 "
Flammability	ASTM E648	Class 1 (≥ 0.45 W/cm ²)
Smoke Density	ASTM E662	< 450
Width	-	144 "
Pattern	-	Solana K0120
Commercial warranty	-	10 year limited
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Installation method	-	Glue-Down
Pattern type	-	Organic
Format Type	-	Roll
Construction	-	Patterned Symtex
Soil protection	-	Application Rate: 2% of Face Weight
Colorfastness to Light	AATCC 16E	≥ 4 after 100 hours
Stitches/Rows per Inch	-	9.60 /in
Pile thickness	ASTM D5848	0.235 " (5.94 mm)
Average pile height	-	0.255 " (7 mm)
Pile density	-	9143 oz/yd ³
Fiber System	-	Dynex SD® Nylon
Dye Method	-	Solution dyed
Secondary backing	-	ERGO-BLOK
Primary backing	-	Woven Polypropylene
Pattern scale	-	Large
Pattern repeat length	-	75 "
Pattern repeat width	-	72 "
Stain Resistance	AATCC 175-08	≥ 8
Pile construction	-	Patterned Tipshear
Surface Flammability	-	Meets CAN/CGSB-4.2 No.27.6/DOC FF 1-70
Electrostatic Propensity	-	≤ 3.5 kV
Gauge	-	1/10"