

## TECHNICAL AND ENVIRONMENTAL SPECIFICATIONS

### CLASSIFICATION

	Standard	Tarkett value
<b>Surface treatment</b>	-	Eco-Ensure(Fluorine-Free Soil Protection)
<b>Flammability</b>	ASTM E648	Class 1 ( $\geq 0.45$ W/cm <sup>2</sup> )
<b>Smoke Density</b>	ASTM E662	< 450
<b>Pattern</b>	-	Solana K0120
<b>Pattern type</b>	-	Organic
<b>Format Type</b>	-	Roll
<b>Commercial warranty</b>	-	10 year limited

### CHARACTERISTICS

	Standard	Tarkett value
<b>Pile thickness</b>	ISO 1766	0.235 " (5.94 mm)
<b>Fiber System</b>	ISO 2424	Dynex SD® Nylon
<b>Format Type</b>	-	Roll
<b>Commercial warranty</b>	-	10 year limited
<b>Construction Process</b>	ISO 2424	TUFTED
<b>Installation method</b>	-	Glue-Down
<b>Surface treatment</b>	-	Eco-Ensure(Fluorine-Free Soil Protection)
<b>Secondary backing</b>	ISO 2424	ERGO-BLOK
<b>Dye Method</b>	-	Solution dyed
<b>Primary backing</b>	-	Woven Polypropylene
<b>Pile construction</b>	-	Patterned Tipshear
<b>Gauge</b>	-	1/10"
<b>Face Weight</b>	-	30 oz/yd <sup>2</sup>
<b>Pile density</b>	ISO 8543	9143 oz/yd <sup>3</sup>
<b>ReStart®</b>	-	Yes
<b>Recycled Content - Production Waste</b>	-	18.2 %
<b>Post Consumer recycled content</b>	-	4.4 %

### TECHNICAL PERFORMANCE

	Standard	Tarkett value
<b>Flammability</b>	-	Class 1 ( $\geq 0.45$ W/cm <sup>2</sup> )
<b>Electrostatic Propensity</b>	-	$\leq 3.5$ kV
<b>Colorfastness to Light</b>	-	$\geq 4$ after 100 hours
<b>Is cuttable</b>	-	Yes

### SUSTAINABILITY, ENVIRONMENT & INDOOR AIR QUALITY

	Standard	Tarkett value
--	----------	---------------

	Standard	Tarkett value
ReStart®	-	Yes
Recycled Content - Production Waste	-	18.2 %
Antimicrobial Chemicals	-	No antimicrobials (EPA Registered pesticides) added to product
Post Consumer recycled content	-	4.4 %

## CHARACTERISTICS & TECHNICAL PERFORMANCE

	Standard	Tarkett value
Type of product	-	Textile Flooring
Length	-	1800 "
Flammability	ASTM E648	Class 1 ( $\geq 0.45$ W/cm <sup>2</sup> )
Smoke Density	ASTM E662	< 450
Width	-	144 "
Pattern	-	Solana K0120
Commercial warranty	-	10 year limited
Surface treatment	-	Eco-Ensure(Fluorine-Free Soil Protection)
Installation method	-	Glue-Down
Pattern type	-	Organic
Format Type	-	Roll
Construction	-	Patterned Symtex
Soil protection	-	Application Rate: 2% of Face Weight
Colorfastness to Light	AATCC 16E	$\geq 4$ after 100 hours
Stitches/Rows per Inch	-	9.60 /in
Pile thickness	ASTM D5848	0.235 " (5.94 mm)
Average pile height	-	0.255 " (7 mm)
Pile density	-	9143 oz/yd <sup>3</sup>
Fiber System	-	Dynex SD® Nylon
Dye Method	-	Solution dyed
Secondary backing	-	ERGO-BLOK
Primary backing	-	Woven Polypropylene
Pattern scale	-	Large
Pattern repeat length	-	75 "
Pattern repeat width	-	72 "
Stain Resistance	AATCC 175-08	$\geq 8$
Pile construction	-	Patterned Tipshear
Surface Flammability	-	Meets CAN/CGSB-4.2 No.27.6/DOC FF 1-70
Electrostatic Propensity	-	$\leq 3.5$ kV
Gauge	-	1/10"