

TECHNICAL AND ENVIRONMENTAL SPECIFICATIONS

CHARACTERISTICS

| | Standard | Tarkett value |
|-----------------------------|----------|---|
| Pile thickness | ISO 1766 | 0.070 " (1.83 mm) |
| Fiber System | ISO 2424 | Dynex SD® Nylon |
| Construction Process | ISO 2424 | TUFTED |
| Installation method | - | Glue-Down |
| Commercial warranty | - | Lifetime Limited |
| Surface treatment | - | Eco-Ensure(Fluorine-Free Soil Protection) |
| Secondary backing | ISO 2424 | ethos® Modular with Omnicoat Technology™ |
| Pile construction | - | Patterned loop pile |
| Gauge | - | 5/64" |
| Face Weight | - | 17 oz/yd ² |
| Pile density | ISO 8543 | 139.50 oz/yd ³ |
| Dye Method | - | Solution dyed |
| Primary backing | - | Synthetic Non-Woven |
| Cradle-to-Cradle | - | Silver |
| DECLARE | - | Yes |

TECHNICAL PERFORMANCE

| | Standard | Tarkett value |
|---------------------------------|----------|-------------------------------------|
| Flammability | - | Class 1 (≥ 0.45 W/cm ²) |
| Electrostatic Propensity | - | ≤ 3.0 kV |
| Is cuttable | - | No |

SUSTAINABILITY, ENVIRONMENT & INDOOR AIR QUALITY

| | Standard | Tarkett value |
|--|----------|--|
| Cradle-to-Cradle | - | Silver |
| ReStart® | - | Yes |
| CRI Green Label Plus Certification | - | GLP8320 |
| DECLARE | - | Yes |
| Recycled Content - Production Waste | - | 22 % |
| Third Party Certification NSF-140 | - | Platinum |
| Antimicrobial Chemicals | - | No antimicrobials (EPA Registered pesticides) added to product |
| Post Consumer recycled content | - | 32 % |

CHARACTERISTICS & TECHNICAL PERFORMANCE

| | Standard | Tarkett value |
|------------------------|----------|------------------|
| Type of product | - | Textile Flooring |
| Pattern | - | Braided 11439 |

| | Standard | Tarkett value |
|---------------------------------|--------------|---|
| Commercial warranty | - | Lifetime Limited |
| Flammability | ASTM E648 | Class 1 (≥ 0.45 W/cm ²) |
| Smoke Density | ASTM E662 | 450 or Less |
| Surface treatment | - | Eco-Ensure(Fluorine-Free Soil Protection) |
| Installation method | - | Glue-Down |
| Pattern type | - | Linear |
| Construction | - | Stratatec Patterned Loop |
| Soil protection | - | Application Rate: 2% of Face Weight |
| Stain Resistance | AATCC 175-08 | ≥ 8 |
| Pile construction | - | Patterned loop pile |
| Surface Flammability | - | Meets CAN/CGSB-4.2 No.27.6/DOC FF 1-70 |
| Electrostatic Propensity | - | ≤ 3.0 kV |
| Gauge | - | 5/64" |
| Stitches/Rows per Inch | - | 10.90 /in |
| Pile thickness | ASTM D5848 | 0.070 " (1.83 mm) |
| Average pile height | - | 0.110 " (3 mm) |
| Pile density | - | 139.50 oz/yd ³ |
| Fiber System | - | Dynex SD® Nylon |
| Dye Method | - | Solution dyed |
| Secondary backing | - | ethos® Modular with Omniccoat Technology™ |
| Primary backing | - | Synthetic Non-Woven |
| Pattern scale | - | Medium |
| Pattern match | - | No |
| Pattern repeat length | - | 75 " |
| Pattern repeat width | - | 72 " |